

TEMPERATURE CONTROLS PTY LTD

ACN: 075 298 592 ABN: 76 075 298 592

7 YAMMA STREET SEFTON, NSW 2162 AUSTRALIA

PHONE: 61 2 9721 8644 FAX: 61 2 9738 9339

INTERNET: www.temperature.com.au EMAIL: sales@temperature.com.au



ISO9001:2000

Lic 14412

THERMOCOUPLES * RTD SENSORS * THERMOWELLS * EXTENSION CABLES * LEVEL SWITCHES

EPOXY PAINTING PROCEDURE

- Item Thermocouple terminal Head
- Surface Preparation Solvent Cleaning
- Product name Epoxy enamel paint #D001-30-0001
- Color Silver or other colours

Procedure

Number of coatings 2

1st Coating

Method of painting Spray

Thickness of dry film 18 - 20 μ

Cool time 20 min

2nd Coating

Method of painting Spray

Thickness of dry film 18 - 20 μ

Cool time 12 – 13 hours

Epoxy paint composition

1. Epoxy Resin 53

2. Pigment 24

3. Additives 1

4. Solvents 2

Total 80

Polyamide 20

MELBOURNE OFFICE: PHONE (03) 9384 0444 FAX: (03) 9384 0204
PROUDLY MANUFACTURING IN AUSTRALIA